

NUKOTE LP

Low Pressure

DESCRIPTION:

Nukote LP is a fast set, rapid curing modified polyurea designed for use in application on concrete, steel or other substrates that do not require the full physical properties of other specially formulated polyurea. Nukote LP is designed for general-purpose use, and performs well in anticorrosion and waterproofing applications on steel, concrete, and many other substrates. Nukote LP can be applied at temperatures ranging from -30°C to 120°C . This aromatic polyurea elastomer displays good chemical resistance, thermal stability and good UV resistance. Nukote LP can be textured easily for anti-skid purposes. The product shows very good moisture permeation resistance and is less sensitive to moisture.

FEATURES

- 100% Solids with zero VOC
- Fast reactivity and cure time resulting in almost immediate return-to-service time
- Can be applied in temperatures from -30°C
- Low temperature flexibility
- Good elongation properties
- Seamless, resilient, flexible and tough
- Chemical Resistant (consult NCSI)
- Good corrosion protection
- Impact, tear and abrasion resistant
- waterproofing membrane
- Low pressure application

TYPICAL USES:

- Truck bed, Trailers and Vehicle liners
- General waterproofing,
- Cargo holds
- Truck Bed Surfaces
- Boat Linings
- Mold castings
- Encapsulation of Fiber glass bodies.

COLORS:

Standard medium grey only, custom colors, blended to match any RAL number, are available upon request subject to minimum quantity. Nukote LP may be top coated with an aliphatic polyurethane/polyurea coating for a colour fast finish within the recoating window.

PACKAGING:

Nukote LP is available in 380 liter sets shipped in metal drums of 190 liters each of Side A and side B or 38 liter kits shipped in plastic pails of 19 liters of side A and 19 liters of side B, or 2090 tote sets shipped in hardened plastic-metal reinforced UN approved totes of 1045 liters each of side A and side B.

PDS

ISSUE DATE
15/11/2009

NUKOTE COATING SYSTEMS INTERNATIONAL LLC
2250 E TROPICANA AVENUE 19-621
LAS VEGAS, NEVADA 89119
USA

WWW.MCS-INTL.NET

NUKOTE LP

Low Pressure

TECHNICAL DATA (All values @25 °C)	
Solids by volume	100%
Volatile Organic Compounds	0 gm/ lit
Theoretical coverage@ 1mm	1m ² / lit
Specific Gravity (kg/ litre)	A-1.056, B-1.052
Viscosity at 70°C in cps (ASTM D 412)	A-400-500, B 700-900
Shelf life @ 25°C	6 to 9 Months
Tensile strength (ASTM D 412 C)	14 to 16MPa
Elongation (ASTM D 412)	200- 300 %
Hardness ASTM D 2240	90 to 93 Shore A
Flexibility (2mm mandrel ASTM 1737)	Pass
Water Vapour Permeability ASTM E 96	0.00034 perm -inch
Water Absorption -24 hours (ASTM D 471)	< 0.5%
Crack Bridging @-25°C (ASTM C 836) , 25 cycles	Pass
Tear strength (Die C ASTM 624) (KN/m)	30-40
Impact Resistance	> 200 lbs
Fire Rating	Class 2
Flash point Pensky Martin	>93°C
Service temperature (Dry)	-30°C to 120°C
Abrasion Resistance (ASTM D 4060)	45 mg loss Taber CS 17 wheel 1Kg/1000 rev
PROCESSING PROPERTIES (Under standard lab conditions)	
Mix Ratio V/V	1:1
Gel time	6 to 8 seconds
Tack free time (DFT & Temperature dependant)	40 to 55 Seconds
Post cure time	24 hours
<i>(The above properties and values are highly dependent on equipment, equipment settings, spray gun, chamber, tipsize, temperature, pressure and related parameters and slight variations are possible). The above values are as per NCSI Standard lab practices & methodology)</i>	

NUKOTE LP

Low Pressure

COVERAGE:

Nukote LP may be applied at any rate to achieve the desired thickness. Calculation for theoretical coverage at 1mm thickness is 1 liter/m².

MIXING:

Nukote LP might not be diluted under any circumstance. Use appropriate solvent for purge line and flushing of equipment and if spraying stops for a period of time in excess of the pot life of the material. Thoroughly mix Nukote LP part B resin material with air driven power equipment until a homogeneous mixture and color is obtained.

SURFACE PREPARATION:

Concrete:

The surface of a concrete subfloor should be dry, smooth, and structurally sound. It should also be free of depression, scale, or foreign deposits of any kind. Remove all curing compounds. Abrasive blast, sweep blast or water blast to remove all laitance and expose all voids. Use a good quality epoxy filler / mortar for blow hole filling, skim coat or repairs. All concrete subfloors on or below grade level should be tested for moisture. On-grade or below-grade concrete floors should have a moisture barrier installed to protect from ground moisture.

Metal:

All surfaces should be clean and free from contamination. The surface should be assessed and treated in accordance with ISO 8504. Abrasive blast the surface to minimum SA 2.5, as per ISO 8501-1, for a visual assessment of surface cleanliness with an anchor profile of 75 -100 microns.

Refer to NCSI surface preparation manual for more details.

APPLICATION:

Nukote LP should be applied using dedicated plural component spray proportioning equipment, such as those manufactured by Glascraft®, Gusmer® and Graco®. The simple spray equipment can have a single motor driving two separate fixed ratio proportioning pumps. Side-A and Side-B are pumped separately to a static mixing tube for air assisted or airless spray. It is recommended to use a 24 element mixing wand/ Static spiral mixer for proper mixing. The proportioning equipment utilized must be capable of supplying correct pressure for the appropriate hose length on a consistent basis. Both Part-A and Part-B material should be preconditioned at 25-30°C before application. For optimum performance, the substrate should be abrasive blasted. Concrete substrates should be allowed to cure a minimum of 30 days. On concrete, Nukote LP should always be applied over a suitable primer for maximum adhesion. Please review your specific project with Nukote technicians. For all submersed applications, a primer is absolutely essential, after proper preparation. Recommended DFTs are a function of the project, please contact a Nukote technician. On horizontal surface applications, a texture “stipple” coat can be applied for non-skid purposes, after reaching the initial desired film thickness.

EQUIPMENT CLEAN UP:

Cured product may be disposed of without any restrictions. The uncured Isocyanate and resin portions should be mixed together and disposed of in a normal manner. “drip-free” containers should be disposed of according to local environmental laws and ordinances.

PDS

ISSUE DATE
15/11/2009

NUKOTE COATING SYSTEMS INTERNATIONAL LLC
2250 E TROPICANA AVENUE 19-621
LAS VEGAS, NEVADA 89119
USA

WWW.MCS-INTL.NET

NUKOTE LP

Low Pressure

STORAGE:

Six to nine months in factory delivered, unopened drums. Keep away from extreme heat, freezing, and moisture. The use of drum heaters is encouraged to reduce material viscosity at low temperatures.

LIMITATIONS:

Do not open until ready to use, and store in a sealed container after opening. Adding a nitrogen blanket is strongly recommended for use on the 'A' component for storage after opening.

WARNING:

This product contains Isocyanate and curatives.

CHEMICAL RESISTANCE:

Each Nukote product formulation has varying levels of resistance to specific chemicals. Please review the chemical immersion test data included in the Nukote Test Book for general resistance to specific chemicals at specific concentration levels. Chemical concentrations are complex and when combined with temperatures above ambient levels this complexity increases exponentially. Contact Nukote Technical Personnel for specific recommendations for chemical resistance prior to specifying these products in this application type. Consult with NCSI for more details on product and chemical resistance. The following chart is the results of Polyurea immersed in chemicals and tested as per ASTM D 3912.

Chemicals	Resistance	Chemicals	Resistance
Hydrochloric acid upto 10%	R	Ammonium Hydroxide 20%	R
Sulphuric Acid 15%	R	Ammonium Hydroxide 50%	RC
Phosporic Acid 10%	R	Pottasium hydroxide 10%	R
Acetic Acid 10%	R	Pottasium hydroxide 20%	RC
Sea water	R	Gasoline	RC
Water @ 80 °C	R	Motor Oil	RC
Diesel Fuel	R	Hydraulic Fluid	RC

R- Resistant, RC – Short term, Slight surface change, discolouration with no loss of hardness.

WARRANTIES AND DISCLAIMERS:

Nukote Coating Systems International, a Nevada, USA Corporation warrants that the two components of this product shall conform to the technical specifications published in the product literature. The quality and fitness of the product is dependent upon the proper mixture and application of the components by the applicator. Nukote Coating Systems has no role in the application of the finished polymer other than to manufacture and supply its two components. It is vital that the person applying this product understands the product and is fully trained and certified in the use of plural component equipment and application of plural component materials. There are no warranties that extend beyond the description on the face of this instrument, except when provided in writing, directly by Nukote Coating Systems International and executed under seal by a company officer.

PDS

ISSUE DATE
15/11/2009

NUKOTE COATING SYSTEMS INTERNATIONAL LLC
2250 E TROPICANA AVENUE 19-621
LAS VEGAS, NEVADA 89119
USA

WWW.MCS-INTL.NET